

Report No. : PN:EE:1556000953

ISSUE DATE : 16/08/2024



AP LANKA (PVT) LTD
416/5, LEYLAND ROAD
HOMAGAMA-10200
LK

CONTACT PERSON : HARSHA DULIP

THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED AND IDENTIFIED BY/ON BEHALF OF THE CUSTOMER AS :

SAMPLE DESCRIPTION HOT DIPPED GALVANIZED CABLE LADDERS
PART NO -782 301

COUNTRY OF ORIGIN SRI LANKA

SAMPLE RECD ON 03/07/2024 **TESTING PERIOD** : 03/07/2024-09/08/2024

TEST(S) REQUESTED SALT SPRAY TEST AS PER IEC 61537 – CLAUSE 14.2.3 – CLASS 7

SALT SPRAY TEST :

TEST METHOD : ISO 9227 : 2022 / ISO 10289 : 1999 /As per customer request.

Test Condition :

Sr. No.	Parameter	Specification
1	Salt Solution Concentration	(50 ± 5) g/l
2	Chamber Temperature	(35 ± 2)°C
3	pH of fog solution	6.5 – 7.2
4	Fog Collection	1.5 ± 0.5 ml/hr
5	Test duration	720 Hours

No.of Test Specimens : 01

Requirement : The sample shall have passed the test,If the corrosion of the surface,according to rating 4 of ISO 10289 : 1999 has not exceed.



Observation :

Test Duration	Observation
24 hrs	White rust.
48 hrs	White rust.
72 hrs	White rust.
96 hrs	White rust.
120 hrs	White rust.
144 hrs	White rust.
168 hrs	White rust.
192 hrs	White rust.
216 hrs	White rust.
240 hrs	White rust.
264 hrs	White rust.
288 hrs	White rust.
312 hrs	White rust.
336 hrs	White rust.
360 hrs	White rust.
384 hrs	White rust.
408 hrs	White rust.
432 hrs	White rust.
456 hrs	White rust.
480 hrs	White rust.
504 hrs	White rust.
528 hrs	White rust.
552 hrs	White rust.
576 hrs	White rust.
600 hrs	White rust.
624 hrs	White rust.
648 hrs	White rust.
672 hrs	White rust.
696 hrs	White rust.
720 hrs	White rust.

JOE No. : 2456800266

Control No.:1556503431

"This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgsgroup.in/Service-Terms> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents a www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. *The laboratory shall be responsible for all the information provided in the report, except when information and instruction for specific scope of testing is provided by the customer.*"

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days from the date of issue of report .The samples from the regulatory bodies are to be retained as specified.This document cannot be reproduced,except in full,without prior written approval of the company. *No decision rule is applied, when comparing the measurement result(s) with the applicable limit(s) according to the specification in the respective standard or as shared by the customer.*